

## TECHNICAL DATA SHEET

Dök.No: ÜRT-TDS-140 Yay.Tar.: 24.04.2008 Rev. No: REVİZYON-05 Rev.Tar.: 09.11.2018

Sayfa: 1/1

PRODUCT	PU SPECIAL SANDING SEALER		
PRODUCT CODE and MIXING RATIO	MIXING RATIO (by weight)	1st COMPONENT	2nd COMPONENT
	2+1	244-0054	219-1032 (summer) 219-1034 (winter)
DESCRIPTION	Solvent based two pack polyurethane sanding sealer system		
APPLICATION AREA	Polyurethane sanding sealer is designed to be used for preparing topcoat applications on all kinds of wood and furniture.		
PROPERTIES	It is designed to be used for hand sanding products like chairs, tables and all kind of wood accessories as it is sanded easily.		
PHSICAL PROPERTIES	Viscosity (D6/25°C) 60" - 65" (WINTER) // 100" - 110" (SUMMER) Density (g/cm3; 20°C) 1±0,05		
DRYING TIME	Pot-Life (hour /20°C, %50 Dust Dry (20°C, %50 hun Touch Dry (20°C, %50 hun Sanding (20°C, %50 hum	nidity)	10 - 15 minutes 90 - 120 minutes
DILUTION RATIO	Varnishes which prepared according to mixing ratios given above are diluted by Kubilay PU thinner by 40-60% as weight.  244-0054  219-1032  2.Component  1 Part  921-0222  PU Thinner  1,5 Part  by weight in delivery form; 1st component:12 kg + 2nd Component:6 kg + PU Thinner:8-9 kg		

## APPLICATION METHOD:

Preperation:Before mixing, first component should be stirred well, then first and second component are mixed according to mixing ratio as much as desired amount, mixture is stridded to obtain a homogenious mixture once again. Finally, for adjusting application viscosity, required amount (according to information which is given in mixin ratio) thinner is added by mixing. Make sure a homogenious mixture is obtained before application.

According to your desire it can be possible to apply Synthetic Wood Protect (113-series), Decocolor Universal Wooden Protect (133-Series), Woodex Concentrate Wood Colorant (123-series) or Aqua-tech Water Based Wood Colorant (013-Series).

After enough drying period depending on the type of the colorant, the sanding sealer has already prepared according to information above can be apply on surfaces by spraying in two-three cross-wise layers. It's recommended as 120 - 140 g/m2 for one layer roughly, although the fact that the degree of surface porosity are important.

Depending on the temp, generaly 3-4 hours later in summer time (one day later for the winter time), can be sand in order first with No:220-280 then No:360-400 for the best results. Then, topcoat varnish application can applied.

## STORAGE:

1st Components will remain stable for at least 12 months and 2nd Components are 6 months when stored in their original packs in a dry place at storage temperatures between 5-35 °C.

It's recommended to read SDS before applications.

Important Note: This information is based on our present state of knowledge and is intended to provide general notes on Kubilay Products and their uses. However without garantee as conditions and methods of end users are beyond our control. We recommend that end users determine the suitability of the materials before adapting them on a commercial scale.