

	TECHNICAL DATA SHEET			Dok.No: ÜRT-TDS-147 Yay.Tar.: 24.04.2008 Rev. No : REVİZYON-03 Rev.Tar. : 12.11.2018 Sayfa : 1/1												
PRODUCT	PU 2K FILLER-S SANDING SEALER															
PRODUCT CODE and MIXING RATIO	MIXING RATIO (by weight)	1st COMPONENT	2nd COMPONENT													
	3+1	274-0063	219-1032													
DESCRIPTION	Solvent based two pack polyurethane sanding sealer system															
APPLICATION AREA	Polyurethane sanding sealer is designed to be used for preparing topcoat applications on all kinds of wood and furniture.															
PROPERTIES	<p>It is highest filling power varnish, designed to provide smooth surfaces such as doors and steel doors by using very special fillers. Due to its special formula, it is very easy and it is sanded in a short time.</p> <p>Not:The transparency may be lost in very thick application, so it's not recommended if transparency is important. Chose another PU sanding sealers from our wide PU sanding sealer portfolio.</p>															
PHSICAL PROPERTIES	Viscosity (D6/25°C) 45" - 50" Density (g/cm3; 20°C) 1±0,05															
DRYING TIME	<table border="0"> <tr> <td>Pot-Life (hour /20°C, %50 humidity)</td> <td>.....</td> <td>2 - 3 hours</td> </tr> <tr> <td>Dust Dry (20°C, %50 humidity)</td> <td>.....</td> <td>15 - 20 minutes</td> </tr> <tr> <td>Touch Dry (20°C, %50 humidity)</td> <td>.....</td> <td>60 - 90 minutes</td> </tr> <tr> <td>Sanding (20°C, %50 humidity)</td> <td>.....</td> <td>2 - 3 hours</td> </tr> </table>				Pot-Life (hour /20°C, %50 humidity)	2 - 3 hours	Dust Dry (20°C, %50 humidity)	15 - 20 minutes	Touch Dry (20°C, %50 humidity)	60 - 90 minutes	Sanding (20°C, %50 humidity)	2 - 3 hours
Pot-Life (hour /20°C, %50 humidity)	2 - 3 hours														
Dust Dry (20°C, %50 humidity)	15 - 20 minutes														
Touch Dry (20°C, %50 humidity)	60 - 90 minutes														
Sanding (20°C, %50 humidity)	2 - 3 hours														
DILUTION RATIO	<p>Varnishes which prepared according to mixing ratios given above are diluted by Kubilay PU thinner by 30% as weight.</p> <table border="0"> <tr> <td>274-0063</td> <td>1.Component</td> <td>.....</td> <td>3 Part</td> </tr> <tr> <td>219-1032</td> <td>2.Component</td> <td>.....</td> <td>1 Part</td> </tr> <tr> <td>921-0222</td> <td>PU Thinner</td> <td>.....</td> <td>1,5 Part</td> </tr> </table> <p><i>by weight in delivery form; 1st component:15 kg + 2nd Component:5 kg + PU Thinner:8-11 kg</i></p>				274-0063	1.Component	3 Part	219-1032	2.Component	1 Part	921-0222	PU Thinner	1,5 Part
274-0063	1.Component	3 Part													
219-1032	2.Component	1 Part													
921-0222	PU Thinner	1,5 Part													
APPLICATION METHOD : <p>Preperation:Before mixing, first component should be stirred well, then first and second component are mixed according to mixing ratio as much as desired amount, mixture is stridded to obtain a homogenous mixture once again. Finally, for adjusting application viscosity, required amount (according to information which is given in mixin ratio) thinner is added by mixing. Make sure a homogenous mixture is obtained before application.</p> <p>According to your desire it can be possible to apply Synthetic Wood Protect (113-series), Decocolor Universal Wooden Protect (133-Series), Woodex Concentrate Wood Colorant (123-series) or Aqua-tech Water Based Wood Colorant (013-Series).</p> <p>After enough drying period depending on the type of the colorant, the sanding sealer has already prepared according to information above can be apply on surfaces by spraying in two-three cross-wise layers. It's recommended as 120 - 140 g/m2 for one layer roughly, although the fact that the degree of surface porosity are important.</p> <p>Depending on the temp, generally 2-3 hours later in summer time (one day later for the winter time), can be sand in order first with No:220-280 then No:360-400 for the best results. Then, topcoat varnish application can applied.</p>																
STORAGE: <p>1st Components will remain stable for at least 12 months and 2nd Components are 6 months when stored in their original packs in a dry place at storage temperatures between 5-35 °C.</p> <p>It's recommended to read SDS before applications.</p>																

Important Note: This information is based on our present state of knowledge and is intended to provide general notes on Kubilay Products and their uses. However without guarantee as conditions and methods of end users are beyond our control. We recommend that end users determine the suitability of the materials before adapting them on a commercial scale.