

	TECHNICAL DATA SHEET		Dök.No: ÜRT-TDS-25 Yay.Tar.: 24.04.2008 Rev. No : REVİZYON-02 Rev.Tar. : 13.11.2018 Sayfa : 1/1
PRODUCT	DECOCOLOR WOOD COLORANT		
PRODUCT CODE	133 - Serie		
DESCRIPTION	Yellow , Brown, Venge, Black etc		
DESCRIPTION	It's concentrated colorans system which can be applied by diluting either water or solvent.		
APPLICATION AREAS	It is used for coloring on wooden veneer or massive surfaces of interior furniture.		
PROPERTIES	High color shade, non-fading and fast drying Easy to apply		
TECHNICAL PROPERTIES	Viscosity (D4/20°C)	13"- 20"	
	Density (20°C)	0,9 -1,8 g/cm3	
DRYING	Diluting with Kubilay Cellulosic Thinner; Dust Dry (20°C, %50 humidity) 3 - 5 minutes Set Dry (20°C, %50 humidity) 15 - 20 minutes Diluting with Water; Dust Dry (20°C, %50 humidity) 10 - 15 minutes Set Dry (20°C, %50 humidity) 90 - 120 minutes		
APPLICATION METHOD: Products should mix well in the can, before application. It is applied on sanded, dry and dust-free wood surfaces diluting with either water or Kubilay Cellulosic Super Thinner (961-0640) and applied by spray, cloth or sponge. Depending on the color tone; Decocolor wood colorant system is used by diluting with water or Kubilay Cellulosic Super Thinner (961-0640) with 1 part Decocolor, 1 - 3 part water or Kubilay Cellulosic Super Thinner (961-0640). Water or Kubilay Cellulosic Super Thinner (961-0640) should not be used together for thinning.			
STORAGE: Products will remain stable for at least 12 months when stored in its original pack in a dry place at storage temperatures between 5-35 °C. It's recommended to read SDS before applications.			

Important Note: This information is based on our present state of knowledge and is intended to provide general notes on Kubilay Products and their uses. However without guarantee as conditions and methods of end users are beyond our control. We recommend that end users determine the suitability of the materials before adapting them on a commercial scale.