



## TECHNICAL DATA SHEET

Dök.No: ÜRT-TDS-252  
Yay.Tar.:23.05.2022  
Rev. No : REVİZYON-00  
Rev.Tar. : 23.05.2022  
Sayfa : 1/1

<b>PRODUCT</b>	<b>MIRROR ONE COAT PAINT</b>						
<b>PRODUCT CODE</b>	<b>402- 7008</b>						
<b>DESCRIPTION</b>	Mirror One Coat based on combination of special synthetic resins with oven drying for copper mirrors.						
<b>COLOR</b>	Grey						
<b>APPLICATION AREAS</b>	Mirror One Coat is designed to be used for final coat applications on primer-based coat which applied on copper mirrors to prevent corrosion. Can be applied spray or curtain.						
<b>PROPERTIES</b>	Good curtain stability , hiding-power and corrosion resistance. It has a good adhesion.						
<b>TECHNICAL PROPERTIES</b>	<table><tr><td>Delivery Viscosity (D4/20°C)</td><td>110 - 120 sec</td></tr><tr><td>Solid Content (%)</td><td>69 ± 1</td></tr><tr><td>Density (gr/cm<sup>3</sup>/20°C)</td><td>1,48 ± 0,05</td></tr></table>	Delivery Viscosity (D4/20°C)	110 - 120 sec	Solid Content (%)	69 ± 1	Density (gr/cm <sup>3</sup> /20°C)	1,48 ± 0,05
Delivery Viscosity (D4/20°C)	110 - 120 sec						
Solid Content (%)	69 ± 1						
Density (gr/cm <sup>3</sup> /20°C)	1,48 ± 0,05						
<b>DILUTION RATIO for Application Viscosity</b>	<p>Approx. 40 sec., D4/20 °C for Curtain Application (can be adjusted by Xylene with %7 dilution ratio)</p> <p><b>Important:</b> It should be stirred well in its pack, then for adjusting application viscosity , required amount (according to information which is given in dilution ratio) thinner is added by mixing. Make sure a homogenous mixture is obtained before application. Products should be diluted as much as required. Those products that long term pre-diluted can lose their homogeneity and cause out of specifications, accordingly.</p>						
<b>APPLICATION METHOD :</b> Before Application, product should be stirred well. Object temperature should be max. 40 °C. Dilute the paint to the application viscosity by required amount (according to information which is given in above) diluent is added. Stir well. Make sure all diluent dissolved in the paint as homogeneously before application. Then applied by curtain coater which is most common way of application for mirror back coating. <b>Consumption;</b> Thickness; approx. 130 g / m <sup>2</sup> – wet - at application viscosity, approx. 25 µm dry film thickness <b>Drying;</b> approx. 4-6 minutes at approx. 130-150 °C object temperature, mirrors should be stacked at object temperatures below 30°C							
<b>STORAGE:</b> Products will remain stable for at least 6 months when stored in its original pack in a dry place by protecting from light at storage temperatures between 5-35 °C. It's recommended to read SDS before applications.							

*Important Note: This information is based on our present state of knowledge and is intended to provide general notes on Kubilay Products and their uses. However without guarantee as conditions and methods of end users are beyond our control. We recommend that end users determine the suitability of the materials before adapting them on a commercial scale.*